

**Plastics piping and
ducting systems —
Thermoplastics pipes
— Determination of
ring flexibility (ISO
13968:2008)**

ICS 23.040.20

National foreword

This British Standard is the UK implementation of EN ISO 13968:2008. It supersedes BS EN 1446:1996 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/88/4, Test methods.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2009

© BSI 2009

ISBN 978 0 580 56653 0

Amendments/corrigenda issued since publication

Date	Comments

English Version

Plastics piping and ducting systems - Thermoplastics pipes -
Determination of ring flexibility (ISO 13968:2008)

Systèmes de canalisations et de gaines en matières
plastiques - Tubes en matières thermoplastiques -
Détermination de la flexibilité annulaire (ISO 13968:2008)

Kunststoff-Rohrleitungs- und Schutzrohrsysteme - Rohre
aus Thermoplasten - Bestimmung der Ringflexibilität (ISO
13968:2008)

This European Standard was approved by CEN on 14 October 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 13968:2008) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2009, and conflicting national standards shall be withdrawn at the latest by April 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1446:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 13968:2008 has been approved by CEN as a EN ISO 13968:2008 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13968 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 13968:1997), which has been technically revised.

Plastics piping and ducting systems — Thermoplastics pipes — Determination of ring flexibility

1 Scope

This International Standard specifies a method for testing the ring flexibility of a thermoplastics pipe having a circular cross-section.

The method enables determination of the deflection, and necessary force, at which physical damage, if any, occurs within the specified diametric deflection.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9969, *Thermoplastics pipes — Determination of ring stiffness*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

ring flexibility

ability of a pipe to resist ring diametric deflection without loss of structural integrity

[EN 13476-1:2007, 3.1.2.10]

4 Principle

The ring flexibility of a pipe is tested by measuring the force and the deflection while deflecting a ring section from the pipe diametrically at a constant speed until at least the specified deflection is achieved or prior fracture has occurred.

Each test piece is monitored during testing and subsequently inspected for signs of several specific types of mechanical failure.

NOTE It is assumed that the following test parameters are set by the standard making reference to this International Standard:

- a) if appropriate, a greater length of the test pieces than the length specified in ISO 9969, see Clause 6;
- b) the deflection, if appropriate, see 8.1.

5 Apparatus

5.1 Compression testing machine, as specified in ISO 9969, but capable of producing at least the specified diametric deflection of the test piece at the applicable speed (see ISO 9969:2007, Table 1).

5.2 Dimensional and force measuring devices, conforming to ISO 9969, but capable of measuring diametric deflections up to at least the specified deflection and the corresponding compressive forces.

6 Test pieces

Prepare three test pieces from a single pipe, as specified in ISO 9969, and designate them a, b, and c respectively. The referring standard may specify longer test pieces than defined in ISO 9969.

7 Conditioning

Condition the test pieces as specified in ISO 9969.

8 Procedure

8.1 Conduct the test in accordance with the procedure given in ISO 9969, but continue compression while measuring the change in either inside diameter or outside diameter until the specified deflection has been achieved. Unless otherwise specified in the referring standard, the deflection shall be 30 % of the outside diameter.

During the compression, monitor for signs of failure (see 8.2), until either the specified deflection has been reached or the test piece has failed, whichever occurs first.

If desired, the deflection may be continued after a failure has occurred or the specified deflection has been reached in order to determine other properties of the pipe.

8.2 For each test piece, prepare a force/deflection graph, and inspect and record the type and the position of each event [a) to e)] with respect to the corresponding force and deflection.

- a) Inspect the force/deflection graph for compliance to the requirements in the referring standard.
- b) Check for any cracking or crazing in any part of the wall structure.
- c) Check for any wall delamination.
- d) Check for any permanent buckling in any part of the structure of the pipe wall.
- e) Make any other observation as specified in the referring standard.

Whitening of the pipe shall not be considered as an indication of one of the above-mentioned mechanical failures.

9 Test report

The test report shall include at least the following information:

- a) a reference to this International Standard and to the referring standard;
- b) the identification of the thermoplastics pipe, including:
 - 1) manufacturer,
 - 2) type of pipe,
 - 3) dimensions,
 - 4) production date,
 - 5) lengths of test pieces,
 - 6) mass per metre length of the pipe;
- c) the test temperature;
- d) the force/deflection graph for each test piece;
- e) where appropriate, the force and deflection at which any of the events specified in 8.2 occurred;
- f) the deflection and force at the maximum point, if a maximum occurred;
- g) any factors which may have affected the results, such as any incidents or any operating details not specified in this International Standard;
- h) the date of test.

Bibliography

- [1] EN 13476-1:2007, *Plastics piping systems for non-pressure underground drainage and sewerage — Structured-wall piping systems of unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 1: General requirements and performance characteristics*

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com